



# Primer Hydro F

## - Deep Primer W -

Water-based primer with a strengthening effect

Availability				
Quantity per pallet	288	90	24	
Packaging unit	1 l	5 l	30 l	
Type of container	Plastic canister	Plastic canister	Plastic canister	
Container code	01	05	30	
Art. no.				
2842	■	■	■	

### Application rate

Approx. 100 - 400 ml/m<sup>2</sup> depending on the substrate



### Range of use



- Wall and floor areas
- Strengthening and priming of mineral substrates on a gypsum or cement base
- Primer for levelling compounds
- Dusting, sanding screed surfaces under coverings

### Property profile



- Strengthens the surface
- Evens out differing absorption behaviour
- Quick drying

### Characteristic data of the product

Density	Approx. 1.02 g/cm <sup>3</sup>
Sd value	< 0.10 m (application rate 0.2 l/m <sup>2</sup> )
pH value	> 8
Appearance	Bluish, opaque liquid
Drying time	1 to 6 hours depending on the application quantity, building material and environmental conditions


The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

### Preparation

- **Substrate requirements**  
Clean, dust-free and capable of supporting a load.



## Directions



## Conditions for use

Temperature of the material, air and substrate: from min. +8 °C to max. +30 °C

Shake well before use.

Apply evenly to the material using a brush, roller or spray.

Repeat process wet-on-wet if necessary.

## Tips on use

Wait for the coat to dry fully before applying subsequent coats.

## Notes

The current technical regulations must be observed.

Deviations from applicable regulations must be agreed separately.

## Tools / Cleaning



Brush, surface brush, lambskin roller, suitable spraying equipment

Clean tools immediately after use with water.

### Remmers tools

- Gloria Hochleistungssprüngerät 410 / 405 T Profiline (4667)
- Gloria Drucksprüher Pro 100 (4668)
- Gloria CleanMaster PERFORMANCE PF 50 (4666)
- Gloria CleanMaster EXTREME EX 100 (4665)
- Flächenstreicher (4540)
- Farbrolle FC (4913)
- Rollerbügel (4449)
- Heizkörperpinsel (4541)

## Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 12 months.

## Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

## Personal protective equipment

Respiratory protection with a particle filter P2 must be worn during spraying, together with protective goggles. Wear suitable protective gloves and clothing.

## Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.



Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.